

Standard Programme Carbon Fibre Braids

Article	Diameter at $\pm 45^\circ$	Weight per metre	Fabric weight g/m^2	Thickness at 50% FV mm	Yield m/Kg
---------	----------------------------	------------------	-----------------------	------------------------	------------

<i>Light weight (3K Fibres)</i>					
A 24/10	5 mm	7 g/m	400	0,46	143
A 36/2	10 mm	11 g/m	350	0,40	91
A 48/10	15 mm	13 g/m	275	0,31	77
A 68/2	20 mm	20 g/m	318	0,35	50
A 96/14	25 mm	27 g/m	345	0,40	37
A 120/1	30 mm	33 g/m	350	0,40	30
A 144/1	40 mm	41 g/m	325	0,37	24

<i>Middle weight (6K Fibres)</i>					
B 24/6	10 mm	13 g/m	410	0,47	77
B 36/1	15 mm	20 g/m	425	0,48	50
B 48/9	20 mm	27 g/m	430	0,48	37
B 68/3	25 mm	38 g/m	480	0,55	26
B 84/2	30 mm	47 g/m	490	0,56	21
B 96/15	40 mm	52 g/m	420	0,48	19
B 96/9	50 mm	54 g/m	340	0,39	19
B 120/7	60 mm	68 g/m	360	0,41	15
B 144/5	70 mm	77 g/m	350	0,40	13
B 96/24	80 mm	108 g/m	430	0,49	9,3
B 120/5	90 mm	135 g/m	480	0,55	7,4
B 120/4	100 mm	139 g/m	500	0,57	7,2
B 144/6	125 mm	159 g/m	410	0,47	6,3

<i>Heavy weight (12K Fibres)</i>					
D 36/7	20 mm	41 g/m	650	0,74	24
D 36/8	25 mm	40 g/m	510	0,58	25
D 48/14	30 mm	54 g/m	570	0,65	18,5
D 68/2	40 mm	77 g/m	610	0,70	13
D 84/1	50 mm	97 g/m	620	0,72	10,3
D 96/29	60 mm	112 g/m	600	0,69	8,9
D 120/2	70 mm	132 g/m	600	0,69	7,6
D 144/10	80 mm	161 g/m	640	0,73	6,2
D 144/11	90 mm	164 g/m	580	0,67	6,1
D 96/33	100 mm	212 g/m	670	0,76	4,7
D 120/3	125 mm	270 g/m	680	0,77	3,7
D 144/5	150 mm	331 g/m	700	0,80	3

All technical information and data contained herein is believed accurate and reliable. However, the accuracy and completeness of this information is not guaranteed and is subject to change without notice. NO WARRANTY, EITHER EXPRESSED OR IMPLIED, is given. Seller shall not be liable for injury, loss or damage either direct or consequential arising out of the use of the data provided herein.

Dr. Nolenslaan 119c, P.O. Box 725, NL-6130AS Sittard, The Netherlands

Phone +31 (0)46 4517280, Fax +31 (0)46 4516185

Web: www.eurocarbon.com Email : eurocarbon@eurocarbon.com